

### MS POLYMER MOISTURE CURING TIMBER FLOORING ADHESIVE

Isocyanate and solvent free, high elastic strength Timber Flooring Adhesive with Moisture Vapour Barrier suitable for bonding Solid and Engineered timber to substrates.



#### AREAS OF APPLICATION

- Over existing Timber flooring
- Particle Board
- Chipboard
- Plywood
- Concrete slabs
- Cured floor levelling compounds
- Ceramic tiles
- Marble
- Steel supports

#### FEATURES

- Contains moisture vapour barrier
- One-step process Saving time & money
- Ready to use – no mixing required
- Wet lay – no flash time needed
- Easy trowelling with a smooth consistency
- Low viscosity
- High filling capacity
- Excellent ridge holding
- Elastic with strong green grab
- Reduces stress on the subfloor
- Odourless, water and solvent free
- Bridges normal sub floor variations
- No dimensional changes in timber flooring
- Bonds all timber types
- Clean up thoroughly with damp watery cloth (pH Neutral) whilst still wet or use a special purpose floor wipe to remove when dry.
- 4mm V Notch Trowel required to achieve moisture vapour barrier
- Coverage approx. 14m<sup>2</sup> dependant on substrate
- No isocyanates, very low VOC
- German DIBt certification

#### TECHNICAL DATA

| Technical Data ( 20°C – 60% R.H.) |                                            |                     |                                                                                                |
|-----------------------------------|--------------------------------------------|---------------------|------------------------------------------------------------------------------------------------|
| Appearance                        | Dense paste<br>Natural oak colour          | Viscosity           | 35000mPas – Brookfield<br>Spindle 7.50 giri/min                                                |
| Trowel size                       | 4mm V Notch                                | Density             | 1.70kg per litre                                                                               |
| Coverage                          | 13 -14 m2 approx dependent<br>on substrate | Shear strength      | 1.2 N/mm <sup>2</sup> according to UNI<br>EN14293                                              |
| Application<br>temperature        | From 10°C to 35°C                          | Residue Temperature | Wipe Immediately after use with<br>a water dampened cloth or use<br>Acouslime Adhesive Remover |

### TECHNICAL DATA (continued)

| Technical Data ( 20°C – 60% R.H.) |                 |               |                                                                                |
|-----------------------------------|-----------------|---------------|--------------------------------------------------------------------------------|
| Laying time                       | 40 – 60 minutes | Tool cleaning | Wipe immediately after use with a water dampened cloth or special purpose wipe |
| Light Traffic                     | 6 – 8 hours     | Storage       | 12 months in original sealed container at temperature >10°C                    |
| Sanding                           | 2 – 3 days      | Package size  | 16 kg tubs                                                                     |

### SURFACE PREPARATION

Prior to installation of the timber flooring, all substrates including concrete slabs, cured floor levelling compounds, existing timber flooring, particleboard, chipboard, plywood or ceramic tiles and marble, must be clean and sound (structurally, no flaking or loose material) and dust free, with no traces of waxy residue, coatings, powder, grease or oil etc. present.

If the subfloor is an existing timber floor the surface must be sanded back to remove any coating and vacuum cleaned to remove dust.

Existing ceramic and marble flooring substrates must be free from oily substances, grease or residues of acid or basic detergents due to cleaning.

Subfloors, where the flooring is only fixed in place by the adhesive, need to be flat to within 3mm beneath a 3m straight edge.

#### Concrete Substrate Moisture Assessment:

Assess RH (Relative Humidity) IN SLAB to determine which Acouslime Moisture Seal is suitable for the site conditions. Acouslime 3 in 1 contains a Moisture Vapour Barrier for up to 85% RH in-slab. If the RH is higher than this, one coat of Acouslime Moisture Seal will need to be applied first for up to 90% RH in slab. Two coats of Acouslime Moisture Seal will be required for readings of 90-98% RH. High readings require investigation as to possible moisture sources and may require more than the slab moisture protection outlined in this data sheet.

**Please refer** to our website for the ‘**Acouslime Complete System**’ for timber flooring installations on concrete.

**PLEASE NOTE:** The product must not be diluted in any manner. Surface preparation, cleaning and careful drying is essential for the adhesive to form a strong lasting bond with the flooring substrate.

Pre-Adhesion tests are strongly advisable before proceeding.

### APPLICATION TEMPERATURE

#### Ambient Temperature

Apply at a temperature between 10°C and 35°C.  
The optimal temperature is between 15°C and 25°C

#### Ambient Humidity

Apply at a humidity between 40% and 80%

### COVERAGE

Approx. 14m<sup>2</sup> per 16 kg tub. Dependent on substrate type, a **4mm V Notch Trowel** is required for the full Moisture Vapour Barrier contained in the adhesive, with a full bed application. Monitor trowel angle and wear to ensure the application rate is maintained.

#### Packaging

16 kg Plastic tub.

### APPLICATION

Solid and engineered timber flooring must be installed to manufacturer's instructions and adhere to ATFA industry standards.

Once the tub has been opened, remove the aluminium foil covering the product and set aside, to reuse later if required

Once the tub has been opened, remove the aluminium foil covering the product and set aside, to reuse later if required.

Apply AcouSlime 3 in 1 adhesive with a **4mm V notch trowel** distributing it evenly to obtain a good 'wetting' of the surface. Proceed with laying the timber flooring within 60 minutes of application to substrate.

A full bed that is correctly applied, will provide moisture vapour protection based on the subfloor moisture levels stated in this TDS.

( Continued on next page )

**APPLICATION (Continued)**

Position the timber flooring in place with the necessary pressure to ensure good contact between the timber flooring and the adhesive. Leave a border of at least 10mm between the timber flooring and the wall; or the requirement indicated by manufacturer's installation instructions for timber flooring being used.

**Cleaning of equipment & dried residue on floor**

Any excess adhesive on the top of the boards should be wiped off thoroughly as you go with a damp watery cloth. (pH. neutral) or a special purpose Adhesive Remover wipe which can also be used to remove any dry residue.

In the case of partial use of the tub, cover the adhesive with the aluminium foil that was set aside when the tub was opened, ensuring it adheres to the product and firmly close the tub lid. The tub must be used generally within a week once opened.

**NOTES**

- **Not for outdoor bonding**
- Avoid exceeding quantity of adhesive.
- Not suitable for bonding Polyethylene and Polypropylene.
- The adhesive is moisture curing so open time and hardening can vary significantly according to environmental conditions
- Can generally be painted over however as there are many types of paint products on the market, we always recommend to check the adhesion of the paints.

**SAFETY RULES**

- **PRODUCT FOR PROFESSIONAL USE**
- Avoid contact with eyes and skin.
- Strictly adhere to what is stated on the labelling and consult Safety Data Sheets before using this product.

**DISPOSAL**

- **DO NOT CONTAMINATE THE ENVIRONMENT**
- **Keep out of waterways**
- Dispose of unused product and empty packaging responsibly in accordance with Australian standards and recycling

MADE IN ITALY



**To be read in conjunction with the  
Safety Data Sheet shown on our website.**

The information contained herein is to the best of our knowledge and belief, accurate and reliable as of the date the data was compiled. However, no representation, warranty, or guarantee is made regarding its accuracy, reliability, or completeness by Acouslime Pty Ltd or any of its affiliates. It is the responsibility of the user to assure the suitability and completeness of such information and any depicted product for the particular use of the user. Acouslime Pty Ltd and its affiliates accept no liability for any loss or damage that may occur from the use of the information or any product depicted. Acouslime Pty Ltd and its affiliates specifically and expressly disclaim any and all warranties, express or implied, including merchantability, fitness for a particular purpose and freedom from claims of infringement of the rights of others associated with the sale or use of any product depicted. Acouslime Pty Ltd and its affiliates further disclaim any liability for consequential or incidental damages of any kind, including lost profits.